

**CLAIMS**

1. A resin composition comprising 5-50 parts by weight of a potassium ionomer (A) of an ethylene-unsaturated carboxylic acid copolymer, 0.5 to 20 parts by weight of an ethylene-unsaturated ester copolymer (B) and 94.5 to 30 parts by weight of a thermoplastic resin (C) other than (A) and (B).
2. The resin composition according to claim 1, wherein the potassium ionomer (A) comprises a potassium ionomer of two or more types of ethylene-unsaturated carboxylic acid copolymers which has an average acid content of 10 to 30 % by weight, has difference in acid contents between the highest content and the lowest content of 1 % by weight or more, and has a neutralization degree by potassium of 60 % or more.
3. The resin composition according to claim 1 or 2, wherein the thermoplastic resin (C) is a polyolefin type resin.
4. A single layer article comprises the resin composition described in any one of claims 1 to 3.
5. A multi-layer article having two or more layers, wherein at least one layer comprises the resin composition described in any one of claims 1 to 3.
6. The multi-layer article according to claim 5, wherein the multi-layer article has a layer comprising a thermoplastic resin (D).
7. The multi-layer article according to claim 6, wherein the thermoplastic resin (D) is an olefin polymer.
8. The multi-layer article described in claims 5 to 7 is used

for film, sheet, bag or blow molded container.

9. The single layer article described in claims 4 is used for film, sheet, bag or blow molded container.